



# FOOD MACHINERY GREASE E. P.



## ◆ SUPERIOR RESISTANCE

FOOD MACHINERY GREASE EP is white in color, odorless and has excellent water-resistant capabilities. Contamination by water, detergents, salt water, or foods such as tomato juice, beer, pineapple juice and citric acid will not alter its grease-like characteristics. Resisting typical “washout”, TRC’s FOOD MACHINERY GREASE EP helps reduce grease consumption and protect vital parts in the most extreme of conditions.

## ◆ EXTREME PRESSURE PROTECTION

Containing an advanced extreme pressure package, TRC’s FOOD MACHINERY GREASE EP provides a cushion of lubricating film between metal parts. This helps prevent metal-to-metal contact and premature wear due to heavy loads. Staying put under the most extreme conditions, when other greases will not, helps FOOD MACHINERY GREASE EP provide equipment with the ultimate in protection and performance.



## ◆ NSF H-1, KOSHER, PAREVE AND HALAL CERTIFIED

FOOD MACHINERY GREASE EP is a shear stable, non-toxic food grade grease. By providing the utmost in lubrication and cleanliness, FOOD MACHINERY GREASE EP definitely promotes the image of purity. Its NSF Registered H-1 rating means it may be used in applications where incidental food contact is possible. It is also certified under Kosher, Pareve and Halal standards.



## ◆ MULTI-PURPOSE

FOOD MACHINERY GREASE EP is a true multi-purpose grease. It’s the absolute must-have grease and is recommended for use in bakeries, bottling plants, meat packing plants, dairies, canneries, organic farms, waste water treatment plants, around waterways, etc. Carefully manufactured for a wide range of applications, FOOD MACHINERY GREASE EP is the answer for a multitude of uses.

# SPECIFICATIONS

## FOOD MACHINERY GREASE E.P.

Product Code	108199	108200
NSF Registration Number	159019	128823
NLGI Grade	#1	#2
Thickener Type	Aluminum Complex	Aluminum Complex
Color	White	White
Texture	Smooth - Light Tack	Smooth - Light Tack

TESTS	ASTM METHOD	TYPICAL RESULTS	TYPICAL RESULTS
Penetration/60 Strokes	D-217	310/340	265/295
Dropping Point, °F.	D-566	500 min.	500 min.
Shear Stability		Excellent	Excellent
Pumpability at 0°F.		Fair-Good	Fair-Good
4 Ball Weld, kg.	D-2596	800	800
Timken OK load passing at	D-2509	50 lb.	50 lb.
Rust	D1743	Pass	Pass
4 Ball Wear, (Scar diameter in mm)	D-2266	0.50	0.50
Maximum Operating Temperature		400°F.	400°F.
Water Washout @ 79°C	D-1264	2% Max.	2% Max.

Handling Information: For safe handling of the product, read the Safety Data Sheet (SDS).



**NSF H1,  
KOSHER, PAREVE  
AND HALAL CERTIFIED**

NSF Registration No. 128823  
Category Code :H1

## TEXAS REFINERY CORP

TEXAS • ONTARIO • SASKATCHEWAN • MEXICO

Toll Free: 1-800-827-0711 • Toll Free Fax: 1-800-582-3329

www.texasrefinery.com • E-mail: lube1@texasrefinery.com

**Made In The U.S.A. Since 1922**

PRINTED IN U.S.A. 2019  
L308200